

STARON®

The information contained herein is provided by Cheil Industries, Inc. and its subsidiaries and affiliates (collectively referred to as "Samsung") for information purposes only and should be used by individuals with technical experience and knowledge in the area. Samsung does not make any representation or warranties of the usefulness or expected result of the information, and does not assume any responsibility whatsoever related to the use of the information. Exclusion of the implied warranties may not apply in certain jurisdictions.

PROPERTIES	TYPICAL RESULTS	TEST PROCEDURE
Tensile strength	6,000 psi	ASTM D 638
Tensile modulus	600,000 psi	ASTM D 638
Flexural strength	10,000 psi	ASTM D 790
Flexural modulus	1,000,000 psi	ASTM D 790
Elongation	0.5%	ASTM D 638
Hardness	92 Rockwell "M" Scale 65 Barcol Impressor	ASTM D 785 ASTM D 2583
Thermal expansion	2.0 x 10 ⁻⁵ in/in F°	ASTM D 696
Gloss (60 Gardner)	Between 5 - 20	NEMA LD-3
Color stability	No change-200hrs	NEMA LD-3
Stain resistance	Pass Rating 41	ANSI Z 124
Abrasion resistance	Pass	ANSI Z 124
Boiling water surface resistance	No effect	NEMA LD-3
High temperature resistance	No effect	NEMA LD-3
IZOD Impact resistance (notched)	0.28 ft.lbf/in	ASTM D 256
Ball drop 1/2" (12.3 mm) sheet	144" w/ 1/2 lb ball, No failure	NEMA LD-3
Fungi and Bacterial resistance	No growth	ASTM G 21, G22
Specific gravity Solid colors Patterned colors	1.72 1.69	ASTM D 792
Water absorption	0.04%, (1/2", 24hrs) 0.11%, (1/8", 24hrs)	ASTM D 570
Flammability Flame spread Smoke density	Class A / Class 1 10 10	UBC 8-1 ASTM E 84 ASTM E 84
Radiant heat resistance	No visual effect	NEMA LD-3
Toxicity	84.4g (Solid Color) 81.8g (Patterned Color)	Pittsburgh Test Protocol (LC50 Test)

TEMPEST®

The information contained herein is provided by Cheil Industries, Inc. and its subsidiaries and affiliates (collectively referred to as "Samsung") for information purposes only and should be used by individuals with technical experience and knowledge in the area. Samsung does not make any representation or warranties of the usefulness or expected result of the information, and does not assume any responsibility whatsoever related to the use of the information. Exclusion of the implied warranties may not apply in certain jurisdictions.

PROPERTIES	TYPICAL RESULTS	TEST PROCEDURE
Tensile strength	3,500 psi	ASTM D 638
Tensile modulus	786,000 psi	ASTM D 638
Flexural strength	6,500 psi	ASTM D 790
Flexural modulus	950,000 psi	ASTM D 790
Elongation	0.5%	ASTM D 638
Hardness	88 Rockwell "M" Scale 54 Barcol Impressor	ASTM D 785 ASTM D 2583
Thermal expansion	2.3 x 10 ⁻⁵ in/in F° 3.6 x 10 ⁻⁵ m/m °C	ASTM D 696
Gloss (60 Gardner)	Between 10 - 75	NEMA LD-3
Color stability	Pass	NEMA LD-3
Stain resistance	Pass	ANSI Z 124
Cleanability & Wear	Pass	ANSI Z 124
Boiling water surface resistance	No effect	NEMA LD-3
High temperature resistance	No effect	NEMA LD-3
IZOD Impact resistance (notched)	0.28 ft.lbf/in	ASTM D 256
Ball drop 1/2" (12.3 mm) sheet	1/2 lb ball No failure, 93+	NEMA LD-3
Fungi and Bacterial resistance	No growth	ASTM G 21, G22
Specific gravity	1.6	ASTM D 792
Water absorption	0.04%, (1/2", 24hrs)	ASTM D 570
Flammability	Class A / Class 1	ASTM E 84 / UBC 8-1
Food Equipment Materials	Approved	NSF/ANSI 51 (Food Zone)